



PAKISTAN COUNCIL OF SCIENTIFIC & INDUSTRIAL RESEARCH

Karachi Laboratories Complex
Off University Road, Karachi-75280

Ref: **15176**
ILD/ATR-1569/04

Date: 18-08-2004

MATERIALS/PRODUCTS EVALUATION


ANALYSIS/TEST REPORT ON SAMPLES DECLARED TO BE: Sealing gum ZSG-12/99
(From M/s Zahabiya Chemicals)
FROM: M/s. Govt. of Pak. Pak. Agricultural Research Council Southern Zone, Agricultural Research Centre


NUMBER OF SAMPLES: 01 RECEIVED ON: 02 -- 06 - 2004
REF: CASE NO: 1569 /04
METHOD AGAINST WHICH TESTED: LAB. CODE: --

RESULTS

S.#.	Test items	Result	Test Method
1.	Density (25°C)	1.45 gm/ml	D1475 D 792
2.	Volatile Content	4.3 %	D2369
3.	Drying Properties:	Touch dry within 5 minutes but remains tacky and pliable.	D1640


(Khalil Ahmad)
S.S.O


(Muhammad Aijaz)
S.O


(Zia-ul-Haq Farooqui)
P.S.O/OIC
Materials Science Research Centre


(Khalid Mahmood)
S.O


(Ahmad Ullah Siddiqui)
J.S.O


(S. Naeem Mahmood)
Director General

PLEASE NOTE THAT: This analytical/test report is based solely on the particular sample(s) supplied by the client and cannot be used for publicity/Advertisement.

1) Sampling has not been performed by the PCSIR representatives; thus PCSIR does not assume and assure that the particular samples received are truly representative of any batch or stock or lot or entire production.

2) While every possible precaution was exercised to ensure accuracy of the results PCSIR does not assume any responsibility for the accuracy of results beyond the limit and scope of the available methods employed and the validity of the result for the purpose(s) for which the results may be used.

3) This report shall not be reproduced in part and the party/parties utilizing it in any way shall be fully responsible for ethical use and proper technical application of the report and all losses/claims which may ensue therefrom. The PCSIR shall be held indemnified, harmless and free from any and all claims.